


8. 鋼包、鐵水包用堇石磚

Pyrophyllite bricks for iron ladles and pouring ladles



指標 Index	名稱牌號 Brand of name		XLS-70	XLS-80	X-DS
	Al ₂ O ₃	%		≤23	≤16
SiO ₂	%		≥70	≥80	80
K ₂ O+Na ₂ O	%		≤0.6		
顯氣孔率 Apparent porosity	%		≤18	≤16	15
體積密度 Bulk density	g/cm ³		≥2.1	≥2.1	2.21
常溫耐壓強度 Cold crushing strength	Mpa		≥21.6	≥28	43.5
0.2Mpa 荷重軟化溫度 Refractoriness under load T ₂	°C		≥1400	≥1400	1350
耐火度 Refractoriness	°C		≥1600	≥1610	
重燒線變化率 Reheat liner change 1350°C × 3h	%				1.30